

## **MATERIAL DATA SHEET**

# H-NBR

### **GENERAL INFORMATION**

H-NBR is an is a hydrogenated acrylonitrile-butadiene rubber commonly known as H-NBR. It has good mechanical properties and good chemical resistance to mineral oils and greases, propane and butane, sulfonated crude oil, water-glycol mixtures and can be used at elevated temperatures. H-HBR is highly ozone, weathering and aging resistant.

## **MECHANICAL | ELECTRICAL | THERMAL PROPERTIES**

Colour:			green
Hardness at 20°:	DIN 53505	Shore A	85 +/-2
Density:	DIN ISO 1183-1	g/cm <sup>3</sup>	1.23
100% Modulus:	DIN 53504	N/mm <sup>2</sup>	> 11
300% Modulus:	DIN 53504	N/mm <sup>2</sup>	1
Tensile strength:	DIN 53504	N/mm <sup>2</sup>	> 17
Elongation at break:	DIN 53504	%	> 170
Rebound resilience:	DIN 53512	%	> 35
Tear strength:	DIN ISO 34-1	N/mm <sup>2</sup>	> 6
Abrasion:	DIN 53516	mm <sup>3</sup>	< 115
Compression set:*	DIN ISO 815-1	%	< 24
Compression set:**	DIN ISO 815-1	%	< 26
Compression set:***	DIN ISO 815-1	%	< 40
Min. service temperature:		°C	- 25
Max. service temperature (short term):		°C	+ 150 (+170)

#### **REMARK**

All test methods and values stated above are corresponding to ASTM | DIN | ISO standards and have been tested on standardized plates in the laboratory. All tests are made under laboratory conditions.

This information does not except our customers to test our products for its suitability for the intended application.

Utilization, processing and application of our products are out of our control and therefore our customers responsibility, also in terms of any protective rights of any third party.

<sup>\*</sup> Compression set @ 23°C, 72 hours, 10% deflexion \*\* Compression set @ 70°C, 24 hours, 20% deflexion

<sup>\*\*\*</sup> Compression set @ 100°C, 24 hours, 20% deflexion